

TECHNICAL DATA SHEET

natura
cup

foopak

Foopak Natura Cup using certified wood sources, with natural shade, OBA-free, and poly-coated board, our Natura Cup offers strong wicking resistance and good barrier performance, as well as uniform rim formation and superior printability, with hygienic manufacturing standards for food and beverage applications, both hot and cold. This product is designed to prevent any liquid seepage on the cutting side.



PRODUCT SPECIFICATION

GRAMMAGE T 410 om-02		THICKNESS ISO 534:2005 (E)		STIFFNESS 15° T 556 om-05			
(g/m ²)	(24" x 36" 500)lb	(µm)	(pt)	CD (gf.cm)	MD (gf.cm)	CD (mNm)	CD (mNm)
190 ± 4%	117 ± 4%	265 ± 4%	10.4 ± 4%	27	66	2.6	6.5
210 ± 4%	129 ± 4%	295 ± 4%	11.6 ± 4%	30	83	2.9	8.1
230 ± 4%	141 ± 4%	320 ± 4%	12.6 ± 4%	39	95	3.8	9.3
240 ± 4%	147 ± 4%	325 ± 4%	12.8 ± 4%	41	105	4.0	10.3
260 ± 4%	160 ± 4%	360 ± 4%	14.2 ± 4%	52	123	5.1	12.1
270 ± 4%	166 ± 4%	375 ± 4%	14.8 ± 4%	65	143	6.4	14.0
280 ± 4%	172 ± 4%	385 ± 4%	15.2 ± 4%	69	154	6.8	15.1
300 ± 4%	184 ± 4%	415 ± 4%	16.3 ± 4%	80	187	7.8	18.4

Tolerance for stiffness 10%

PROPERTY	UNIT	METHOD	SIDE	VALUES
Moisture Content	%	T 412 om-02		7.5 ± 1.0
Brightness D65/10°	%	ISO 2470-2:2008 (E)	TOP	Min 80.0
			BACK	Min 80.0
Internal Bonding	J/m ²	T 569 pm-00		Min 150
Water Absorption COBB (180s)	g/m ²	T 441 om-04	TOP	Max 70
Edge Wick	kg/m ²	Internal Mill	Lactic Acid 1%, 1 Hours	Max 1.60
Edge Wick	mm	Internal Mill	Hot water 95° C, 10 Minutes	Max 5
Dirt Spot	Pcs/m ²	T 537 om-02	Spot size, mm ² 0.1 - 0.3	Max 60
			Spot size, mm ² 0.3 - 1.5	Max 10
			Spot size, mm ² > 1.5	Max 0
Surface Tension	Dyne/cm	ASTM D2578-09	PE Side	Min 38

*) Testing is done when production finished at room condition, Temp (°C) : 23 ± 1 and RH (%) : 50 ± 2

LDPE POLY CONFIGURATIONS

GSM, gram/m ²	±2	15	18	20	22	24
THICKNESS, µm	Min	12	15	18	20	22

- Available in both [FS] single-sided and [FZ] double-sided poly configuration, in choice of gloss or matte finish.
- Surface treatment is normally applied for improvement printability, customer may make special request for no treatment.
- PE coated weight and thickness is to be added in baseboard to get final.

APPLICATION USES

- 1/s PE for hot cup application : Hot Beverage, Noodle, Soup Cups, Food Bucket.
- 2/s PE for cold cup application : Cold Beverage, Ice Cream, Yoghurt Cup.

RECOMMENDED PRINTING METHODS

- Offset lithographic
- Flexographic

*) Remarks: recommended to seek further technical advice and support from the ink vendors in term of the quality compliance between printing inks, printing methods and its paperboard.



Does your paper have this?
Use MP (prior) and FSC (prior) to certify your paper.
www.asiapulp.com

#foopakpaper @foopakpaper

Rev.02

Issue Date : March 09, 2021

All parameters measured to 95% confidence interval



SCAN ME

Specification for reference only for update and further information please visit us at :
www.foopak.com | LinkedIn : foopak | Instagram : @foopak.id | Facebook : foopak | email : ask_foopak@app.co.id