





















| GRAMMAGE T410 om-02 | | THICKNESS ISO 534:1988 (E) | | STIFFNESS 15° T 556 om-05 | | | |
|------------------------|-------------------|-------------------------------|-----------|-------------------------------------|---------------|-------------|-------------|
| (g/m²) | (24" x 36" 500)lb | (µm) | (pt) | CD (gf.cm) | MD (gf.cm) | CD (mNm) | CD (mNm) |
| 235 ± 5% | 144 ± 5% | 350 ± 4% | 13.8 ± 4% | 61 | 121 | 6.0 | 11.9 |
| 250 ± 5% | 154 ± 5% | 380 ± 4% | 14.9 ± 4% | 83 | 149 | 7.1 | 14.6 |
| 265 ± 5% | 163 ± 5% | 410 ± 4% | 16.1 ± 4% | 94 | 174 | 8.1 | 17.2 |
| 285 ± 5% | 175 ± 5% | 450 ± 4% | 17.7 ± 4% | 116 | 220 | 11.4 | 21.6 |
| 310 ± 5% | 190 ± 5% | 500 ± 4% | 19.7 ± 4% | 149 | 275 | 14.6 | 27.0 |
| 335 ± 5% | 206 ± 5% | 550 ± 4% | 21.7 ± 4% | 176 | 330 | 17.3 | 32.4 |
|) 365 ± 5% | *) 224 ± 5% | 600 ± 4% | 23.6 ± 4% | 223 | 380 | 21.8 | 33.8 |

^{*)} Available upon requested

cake, pizza and any fried foods.

Tolerance for stiffness 10%

| PROPERTY, UNIT | UNIT | METHOD | SIDE | VALUES |
|------------------------------|------|---------------------|------|------------|
| Moisture Content | % | T 412 om-02 | | 6.0 ± 1.0 |
| Roughness | μm | T 555 om-04 | TOP | Max 1.80 |
| Brightness | % | ISO 2470-2:2008 (E) | TOP | 90.0 ± 1.0 |
| Gloss 75° | % | T 480 om-05 | TOP | 50.0 ± 5 |
| Internal Bond Strength | J/m² | T 569 pm-00 | | Min 120 |
| Water Absorption COBB (60s) | g/m² | T 441 om-04 | TOP | 35-55 |
| Water Absorption COBB (180s) | g/m² | T 441 om-04 | TOP | Max 70 |

APPLICATION USES

- Kit 6, 8 : Chocolate, Cake, Bread, Take-Away Box
- Kit 10: Frozen Cake, Frozen Bread, Food Tray, Take Away Box

COATING OPTIONS

- Available Kit 6, 8, 10
- Kit 6, 8: Waterbase Glue
- Kit 10 : Special Acrylic & Hotmelt Glue

APP sinarmas





RECOMMENDED PRINTING METHODS

- Offset lithographic
- Letterpress

OTHER FEATURE

 Minimum Moisture Evaporation, Very good dimensional stability, Grease resistant (to Kit 10), Environment Friendly, BfR XXXVI compliance.



